


ALSAN® RS COLOR ADDITIVE

Resin Pigment for Surfacing Options



APPLICATIONS

ROOFING

WATERPROOFING

PRODUCT DATA SHEET PD10346 - REV 230817

PRODUCT NUMBERS:

- AC-101 - 1.5 kg Pouch - Signal white
- AC-102 - 1.5 kg Pouch - Light grey
- AC-103 - 1.5 kg Pouch - Pebble grey
- AC-104 - 1.5 kg Pouch - Window grey
- AC-105 - 1.5 kg Pouch - Stone grey
- AC-106 - 1.5 kg Pouch - Beige
- AC-107 - 1.5 kg Pouch - Terra cotta
- AC-108 - 1.5 kg Pouch - Traffic yellow
- AC-109 - 1.5 kg Pouch - Pale green
- AC-110 - 1.5 kg Pouch - Traffic green
- AC-111 - 1.5 kg Pouch - Traffic blue
- AC-112 - 1.5 kg Pouch - Traffic red
- AC-113 - 1.5 kg Pouch - Traffic black
- AC-114 - 1.5 kg Pouch - Traffic grey

*Special order colors are available upon request with required batch minimum.

DESCRIPTION & FEATURES:

ALSAN RS COLOR ADDITIVE is mixed with ALSAN RS 285 CF, ALSAN TRAFIK RS 789 LT and ALSAN TRAFIK RS 787 CF unpigmented resins. **ALSAN RS COLOR ADDITIVE** is supplied in pre-measured 1.5 kg pouches.

- Pre-measured for easy application
- Stocked in 14 standard colors and available in any color with special order requirements
- Non-toxic, Low odor
- Readily mixes into ALSAN RS & ALSAN TRAFIK RS surfacing resins

AVAILABLE COLORS:



NOTE: Color swatches are for representation only and a test patch should be applied to verify a color match. Physical color samples are available upon request.

MIXING INSTRUCTIONS

One pouch of **ALSAN RS COLOR ADDITIVE** is required for each container of ALSAN liquid resin.

The ALSAN liquid resin should be thoroughly mixed before adding the color additive. Using a slow-speed (200-400 rpm) mechanical agitator, mix the liquid resin for 2 - 5 minutes.

Next, add the entire contents of **ALSAN RS COLOR ADDITIVE** to the liquid resin and continue mixing for 2 - 5 minutes until uniform streak-free color is achieved.

NOTE: Combining the color additive to ALSAN RS and ALSAN TRAFIK RS resins does not affect pot life or cure time of the product.

Refer to the ALSAN RS Roofing or ALSAN TRAFIK RS Waterproofing Technical Manuals for additional application guidelines.

STORAGE:

Pouches should be stored in a cool, dry indoor environment at temperatures between 55 - 80°F (13 - 27°C). **PROTECT FROM FREEZING.** Approximate shelf life is 12 months from date of shipment when properly stored, sealed and unmixed.


WARRANTY:

For more information refer to www.SOPREMA.us or contact your SOPREMA representative.



ALSAN® RS COLOR ADDITIVE

Resin Pigment for Surfacing Options



APPLICATIONS

ROOFING

WATERPROOFING

PRODUCT DATA SHEET PD10346 - REV 230817

SUSTAINABILITY



VOC CONTENT
LOW EMITTING

< 5 g/L

COOL ROOF RATING

PRODUCT	RAL #	SOLAR REFLECTANCE	THERMAL EMITTANCE	SRI
Signal white	9003	0.837	0.89	112.1
Light grey	7035	0.486	0.89	56.2
Pebble grey	7032	0.326	0.89	34.8
Window grey	7040	0.318	0.89	33.8
Stone grey	7030	0.204	0.89	19.0
Beige	1001	0.456	0.89	52.1
Terra cotta	2001	0.273	0.89	27.9
Traffic yellow	1023	0.669	0.89	81.3
Pale green	6021	0.314	0.89	33.3
Traffic green	6024	0.293	0.89	30.5
Traffic blue	5017	0.351	0.89	38.1
Traffic red	3020	0.550	0.89	64.9
Traffic black	9017	0.048	0.89	-0.8
Traffic grey	7043	0.069	0.89	1.8