

# ELASTOPHENE® FLAM HR 3.0

High-Resistance, Heat-Welded SBS-Modified Bitumen Membrane



APPLICATIONS

ROOFING

PRODUCT DATA SHEET PDS10027 - REV 230109

## PRODUCT NUMBERS:

- 00252 - 32.8 ft x 39.4 in (10.0 x 1.0 m) - Roll

## DESCRIPTION & FEATURES:

**ELASTOPHENE FLAM HR 3.0** (high-resistance) is a SBS-modified bitumen membrane approved for use in roofing assemblies as a base ply. **ELASTOPHENE FLAM HR 3.0** is reinforced with a glass scrim that is saturated and coated on both sides with a proprietary formulation of elastomeric styrene-butadiene-styrene (SBS) polymer modified bitumen.

- SBS rubber polymer enhances the asphalt blend adding elongation, elasticity and flexibility to the sheet
- Reinforced with a glass scrim that increases the membrane's strength and durability
- Surfaced and backed with a polyolefin burn-off film to optimize heat welding
- Meets or exceeds requirements of ASTM D6163, Type II, Grade S

## USES:

**ELASTOPHENE FLAM HR 3.0** is used as a component in the following systems.

USE	OVERLYING MATERIAL
Field Base Ply	Heat-Welded Modified Bitumen <sup>1</sup>

<sup>1</sup> Refer to SOPREMA's SBS-Modified Bitumen Roofing Membrane Technical Manual

## APPLICATION:



Prior to installation, unroll **ELASTOPHENE FLAM HR 3.0** onto the roof surface and allow to relax. Position **ELASTOPHENE FLAM HR 3.0** in desired position and back roll the product. **ELASTOPHENE FLAM HR 3.0** is then heat welded to approved substrates.

Refer to the SOPREMA SBS-Modified Bitumen Membrane Roofing Technical Manual for complete application guidelines.

## STORAGE:

Store rolls in an upright position to prevent damage. Store in a clean, dry location and cover as necessary to protect from environmental damage such as extreme cold, heat or moisture.

## TESTING & APPROVALS:



## WARRANTY:

For more information refer to [www.SOPREMA.us](http://www.SOPREMA.us) or contact your SOPREMA representative.

# ELASTOPHENE® FLAM HR 3.0

High-Resistance, Heat-Welded SBS-Modified Bitumen Membrane



APPLICATIONS

ROOFING

PRODUCT DATA SHEET PDS10027 - REV 230109

## TECHNICAL INFORMATION & TESTING:

### SHEET PROPERTIES

PROPERTY	VALUE
<b>Elastomeric bitumen</b>	Proprietary blend of bitumen and SBS polymers
<b>ASTM Standard</b>	D6163, Type II, Grade S
<b>Reinforcement</b>	Glass scrim
<b>Top surfacing</b>	Polyolefin film
<b>Back surfacing</b>	Polyolefin film

### DIMENSIONS & MASS

PROPERTY	VALUE	ASTM TEST METHOD
<b>Length</b> , ft (m)	32.8 (10.0)	D5147
<b>Width</b> , in (m)	39.4 (1.0)	D5147
<b>Coverage</b> ,* ft <sup>2</sup> (m <sup>2</sup> )	97.9 (9.1)	D5147
<b>Roll weight</b> , lb (kg)	81 (36.7)	D5147
<b>Rolls per pallet</b>	30	D5147
<b>Pallet weight</b> , lb (kg)	2,480 (1,125)	D5147
<b>Thickness</b> , mils (mm)	118 (3.0)	D5147
<b>Net mass per unit area</b> , lb/100 ft <sup>2</sup> (g/m <sup>2</sup> )	75.3 (3,674)	D5147
<b>Bottom coating thickness</b> , mils (mm)	≥ 40 (1.0)	D5147

\*Coverage rate as reported assumes installation using side and end lap recommendations.

### PHYSICAL PROPERTIES

PROPERTY	MD	XMD	ASTM TEST METHOD
<b>Peak load @ 0°F (-18°C)</b> , lbf/in (kN/m)	185 (32.5)	165 (28.9)	D5147
<b>Elongation at peak load @ 0°F (-18°C)</b> , %	6	6	D5147
<b>Peak load @ 73.4°F (23°C)</b> , lbf/in (kN/m)	110 (19.4)	105 (18.5)	D5147
<b>Elongation at peak load @ 73.4°F (23°C)</b> , %	10	10	D5147
<b>Ultimate Elongation @ 73.4°F (23°C)</b> , %	60	45	D5147
<b>Tear strength @ 73.4°F (23°C)</b> , lbf (N)	180 (801)	190 (845)	D5147
<b>Low temperature flexibility</b> , °F (°C)	-15 (-26)	-15 (-26)	D5147
<b>Dimensional stability</b> , %	< 0.1	< 0.1	D5147
<b>Compound stability</b> , °F (°C)	240 (116)	240 (116)	D5147

Data is represented by average values, unless noted otherwise.