


ELASTOPHENE® FLAM HR FR GR

High-Resistance, Fire Retardant, Granulated SBS-Modified Bitumen Membrane



APPLICATIONS

ROOFING

PRODUCT DATA SHEET DS10029 - REV 230109

PRODUCT NUMBERS:

- 01198 - **32.8 ft x 39.4 in (10.0 x 1.0 m) - Roll Standard white granules (WH)**
- 05014 - **32.8 ft x 39.4 in (10.0 x 1.0 m) - Roll Highly reflective white granules (SG)**

Contact SOPREMA® Customer Service or your sales representative for other granule color options and special order requirements.

DESCRIPTION & FEATURES:

ELASTOPHENE FLAM HR FR GR (high-resistance, fire retardant, granules) is a SBS-modified bitumen membrane approved for use in roofing assemblies as a cap ply.

ELASTOPHENE FLAM HR FR GR is reinforced with a glass scrim that is saturated and coated on both sides with a proprietary formulation of elastomeric styrene-butadiene-styrene (SBS) polymer modified bitumen.

- SBS rubber polymer enhances the asphalt blend adding elongation, elasticity and flexibility to the sheet
- Reinforced with a glass scrim that increases the membrane's strength and durability
- Granule surfacing provides added resistance to weathering and foot traffic
- Backed with a polyolefin burn-off film to optimize heat welding
- Meets or exceeds requirements of ASTM D6163, Type II, Grade G

USES:

ELASTOPHENE FLAM HR FR GR is used as a component in the following systems:

USE	OVERLYING MATERIAL
Field Cap Ply ¹	N/A

¹ Refer to SOPREMA's SBS-Modified Bitumen Roofing Membrane Technical Manual

APPLICATION:



HEAT
WELDED

Prior to installation, unroll **ELASTOPHENE FLAM HR FR GR** onto the roof surface and allow to relax. Position **ELASTOPHENE FLAM HR FR GR** in desired position and back roll the product. **ELASTOPHENE FLAM HR FR GR** is then heat welded to approved substrates.


Refer to the SOPREMA SBS-Modified Bitumen Membrane Roofing Technical Manual for complete application guidelines.

STORAGE:

Store rolls in an upright position to prevent damage. Store in a clean, dry location and cover as necessary to protect from environmental damage such as extreme cold, heat or moisture.

ELASTOPHENE® FLAM HR FR GR

High-Resistance, Fire Retardant, Granulated SBS-Modified Bitumen Membrane



APPLICATIONS

ROOFING

PRODUCT DATA SHEET DS10029 - REV 230109

TECHNICAL INFORMATION & TESTING:

SHEET PROPERTIES

PROPERTY	VALUE
Elastomeric bitumen	Proprietary blend of bitumen and SBS polymers
ASTM Standard	D6163, Type II, Grade G
Reinforcement	Glass scrim
Top surfacing	Ceramic coated granules
Back surfacing	Polyolefin film
Selvage surfacing	Polyolefin film
Selvage width, in (mm)	3 (76)

DIMENSIONS & MASS

PROPERTY	VALUE	ASTM TEST METHOD
Length, ft (m)	32.8 (10.0)	D5147
Width, in (m)	39.4 (1.0)	D5147
Coverage,* ft ² (m ²)	97.9 (9.1)	D5147
Roll weight, lb (kg)	103 (46.6)	D5147
Rolls per pallet	25	D5147
Pallet weight, lb (kg)	2,679 (1,215)	D5147
Thickness, mils (mm)	146 (3.7)	D5147
Thickness @ selvage, mils (mm)	98 (2.5)	D5147
Net mass per unit area, lb/100 ft ² (g/m ²)	96 (4,674)	D5147
Bottom coating thickness, mils (mm)	≥ 40 (1.0)	D5147

*Coverage rate as reported assumes installation using side and end lap recommendations.


PHYSICAL PROPERTIES

PROPERTY	MD	XMD	ASTM TEST METHOD
Peak load @ 0°F (-18°C), lbf/in (kN/m)	185 (32.5)	165 (28.9)	D5147
Elongation at peak load @ 0°F (-18°C), %	6	6	D5147
Peak load @ 73.4°F (23°C), lbf/in (kN/m)	110 (19.4)	105 (18.5)	D5147
Elongation at peak load @ 73.4°F (23°C), %	10	10	D5147
Ultimate Elongation @ 73.4°F (23°C), %	60	45	D5147
Tear strength @ 73.4°F (23°C), lbf (N)	180 (801)	190 (845)	D5147
Low temperature flexibility, °F (°C)	-15 (-26)	-15 (-26)	D5147
Dimensional stability, %	< 0.1	< 0.1	D5147
Compound stability, °F (°C)	240 (116)	240 (116)	D5147
Granule embedment, g	1.5 avg; 2.0 max for SG		D5147

Data is represented by average values, unless noted otherwise.

ELASTOPHENE® FLAM HR FR GR

High-Resistance, Fire Retardant, Granulated SBS-Modified Bitumen Membrane



APPLICATIONS

ROOFING

PRODUCT DATA SHEET DS10029 - REV 230109

SUSTAINABILITY



COOL ROOF RATING

PRODUCT	SOLAR REFLECTANCE		THERMAL EMITTANCE		SRI	
ELASTOPHENE FLAM HR FR GR Standard white granules (WH)	0.26 initial	0.23 3 year	0.90 initial	0.89 3 year	25 initial	23 3 year
ELASTOPHENE FLAM HR FR GR Highly reflective white granules (SG)	0.70 initial	0.62* 3 year	0.90 initial	0.90* 3 year	86 initial	75* 3 year

* CRRG Rapid Ratings. Refer to Cool Roof Ratings Council (CRRG).

TESTING & APPROVALS:



WARRANTY:

For more information refer to www.SOPREMA.us or contact your SOPREMA representative.