

ELASTOPHENE® PS 3.0

SBS-Modified Bitumen Membrane

PRODUCT DATA SHEET PDS10034 - REV 230106



APPLICATIONS

ROOFING

PRODUCT NUMBERS:

- 00504 - 32.8 ft x 39.4 in (10.0 x 1.0 m) - Roll

DESCRIPTION & FEATURES:

ELASTOPHENE PS 3.0 (polyolefin, sanded) is a SBS-modified bitumen membrane approved for use in roofing assemblies as a base ply. **ELASTOPHENE PS 3.0** is reinforced with a glass fiber mat that is saturated and coated on both sides with a proprietary formulation of elastomeric styrene-butadiene-styrene (SBS) polymer modified bitumen.

- SBS rubber polymer enhances the asphalt blend adding elongation, elasticity and flexibility to the sheet
- Reinforced with a glass fiber mat that increases the membrane's strength and durability
- Surfaced with a polyolefin burn-off film to optimize heat welding
- Sanded-backside surfacing improves bonding strength between system layers
- Meets or exceeds requirements of ASTM D6163, Type I, Grade S


USES:

ELASTOPHENE PS 3.0 is used as a component in the following systems.

USE	OVERLYING MATERIAL
Field Base Ply	Heat-Welded Modified Bitumen ¹

¹ Refer to SOPREMA's SBS-Modified Bitumen Roofing Membrane Technical Manual

APPLICATION:



COLD
ADHESIVE



HOT
ASPHALT

Prior to installation, unroll **ELASTOPHENE PS 3.0** onto the roof surface and allow to relax. Place **ELASTOPHENE PS 3.0** in desired position and back roll the product. Apply approved cold adhesive or hot asphalt following the manufacturer specifications. **ELASTOPHENE PS 3.0** is then placed into the cold adhesive or hot asphalt and rolled with a weighted roller to ensure adhesion. Subsequent approved inter-ply or cap ply membranes are applied to **ELASTOPHENE PS 3.0** via heat welding.

Refer to the SOPREMA SBS-Modified Bitumen Membrane Roofing Technical Manual for complete application guidelines.

STORAGE:

Store rolls in an upright position to prevent damage. Store in a clean, dry location and cover as necessary to protect from environmental damage such as extreme cold, heat or moisture.

TESTING & APPROVALS:



FLORIDA BUILDING CODE

MIAMI-DADE COUNTY
APPROVED

NOA # 20-0825.11



HUD MR 1340



LARR # 26062



WARRANTY:

For more information refer to www.SOPREMA.us or contact your SOPREMA representative.



ELASTOPHENE® PS 3.0

SBS-Modified Bitumen Membrane



APPLICATIONS

ROOFING

PRODUCT DATA SHEET PDS10034 - REV 230106

TECHNICAL INFORMATION & TESTING:

SHEET PROPERTIES

PROPERTY	VALUE
Elastomeric bitumen	Proprietary blend of bitumen and SBS polymers
ASTM Standard	D6163, Type I, Grade S
Reinforcement	Glass fiber
Top surfacing	Polyolefin film
Back surfacing	Sanded
Selvage surfacing	Sanded
Selvage width, in (mm)	3 (76)

DIMENSIONS & MASS

PROPERTY	VALUE	ASTM TEST METHOD
Length, ft (m)	32.8 (10.0)	D5147
Width, in (m)	39.4 (1.0)	D5147
Coverage,* ft ² (m ²)	97.9 (9.1)	D5147
Roll weight, lb (kg)	94 (42.6)	D5147
Rolls per pallet	30	D5147
Pallet weight, lb (kg)	2,870 (1,302)	D5147
Thickness, mils (mm)	118 (3.0)	D5147
Thickness @ selvage, mils (mm)	83 (2.1)	D5147
Net mass per unit area, lb/100 ft ² (g/m ²)	87 (4,264)	D5147
Bottom coating thickness, mils (mm)	≥ 40 (1.0)	D5147

*Coverage rate as reported assumes installation using side and end lap recommendations.

PHYSICAL PROPERTIES

PROPERTY	MD	XMD	ASTM TEST METHOD
Peak load @ 0°F (-18°C), lbf/in (kN/m)	115 (20.1)	100 (17.6)	D5147
Elongation at peak load @ 0°F (-18°C), %	4	4	D5147
Peak load @ 73.4°F (23°C), lbf/in (kN/m)	50 (8.8)	40 (7.0)	D5147
Elongation at peak load @ 73.4°F (23°C), %	5	4	D5147
Ultimate Elongation @ 73.4°F (23°C), %	65	65	D5147
Tear strength @ 73.4°F (23°C), lbf (N)	60 (267)	60 (267)	D5147
Low temperature flexibility, °F (°C)	-15 (-26)	-15 (-26)	D5147
Dimensional stability, %	< 0.1	< 0.1	D5147
Compound stability, °F (°C)	250 (121)	250 (121)	D5147

Data is represented by average values, unless noted otherwise.