

INSONO

AF3-47

PRODUCT DATA SHEET

DESCRIPTION & FEATURES

INSONO AF3-47 is composed of self-adhesive elastomeric bitumen with an exposed non-woven polyester reinforcement. The underside is surfaced with a protective release film. INSONO AF3-47 is designed for use under ceramic tiles but can also be installed with wood flooring or vinyl planks. INSONO AF3-47 offers sound damping, crack insulation through a concrete slab and waterproofing.

STORAGE

Store rolls on end and maintain in an upright position to prevent damage. Store rolls in a clean dry location and cover as necessary to protect rolls from environmental damage such as extreme cold, heat, or moisture.

APPLICATION

Prepare surface with INSONO AF3 Primer, ELASTOCOL® Stick H₂O or RESISTO H₂O Primer, follow drying times indicated on the primer data sheet then install the INSONO AF3-47 membrane. Apply the polymer-modified mortar and install the ceramic tiles. For installations where waterproofing is required, waterproofing strips, such as SOPRASEAL® Stick 1100 must be installed prior to INSONO AF3-47.

APPLICATION



SELF-ADHERED

QUICK FACTS

THICKNESS (mils)	WEIGHT (lbs)	DIMENSIONS (ft)
47 (1.2 mm)	37 (17 kg)	3.25 x 55 (1 x 16.76 m)



SOPREMA®

www.soprema.us
 310 Quadral Drive, Wadsworth, Ohio 44281
 Toll Free: (800) 356-3521 | Tel: (330) 334-0066

TECHNICAL INFORMATION & TESTING

PROPERTIES	
Surface	Non-woven polyester
Underface	Silicone release film
Thickness, mils (mm)	47 (1.2)
Dimensions, ft (m)	3.25 x 55 (1 x 16.76)
Weight, lbs (kg)	37 (17)

TECHNICAL PROPERTIES			
PROPERTY	STANDARDS	INSONO AF3-130	
Crack-resistant test	ANSI 118.12-2010; par. 5.4	PASS	
Moisture resistant	ANSI A118.12.-4.1.2	PASS	
Maximum load	ASTM D5147 Tensile/Elongation	MD	XMD
		9 kN/m	5 kN/m
Elongation at maximum load		35%	35%
Elongation break		50%	60%
Cold temperature flexibility, -40°F (-40°C)	ASTM D5147	PASS	
Tear strength	ASTM D4073	380 N	265 N
Water vapor transmission (dry method)	ASTM E96	3.3 ng/Pa•s•m ² (0.025 perm)	

MD: Machine direction XMD: Cross machine direction
(all values are nominal)

TESTING & APPROVALS

ROBINSON TEST

ASSEMBLY

- 12 in x 12 in (30 cm x 30 cm) ceramic tiles with sand and polymer grout (½ in joints)
- Polymer modified mortar
- INSONO AF3-47 membrane applied to substrate
- Primer: SOPREMA ELASTOCOL Stick H₂O or RESISTO H₂O Primer
- 2 inch thick concrete slab

RESULT

Cycle 6 or 7: Residential and Light commercial (Office space, reception areas, kitchen and bath).

ACOUSTIC PROPERTIES

ASSEMBLIES	LABORATORY TESTS		FIELD TESTS	
	STC ⁽¹⁾	IIC ⁽²⁾	ASTC ⁽³⁾	AIIC ⁽⁴⁾
INSONO AF3-47 + ceramic tiles + concrete slab 8 in (20 cm)	-	-	58	30
INSONO AF3-47 + ceramic tiles + concrete slab 8 in (20 cm) + drop ceiling (1 gypsum board 5/8 in (15.9 mm))	-	-	60	39

(1) STC: Standard test method for laboratory measurement of airborne sound transmission loss of building partition. Tests in compliance with the ASTM E90-09 standard.

(2) IIC: Standard test method for laboratory measurement of impact sound transmission through floor-ceiling assemblies using the taping machine. Tests in compliance with the ASTM E492-09 standard.

(3) ASTC (FSTC): Field Sound Transmission Class. Tests in compliance with the ASTM E336-11 and ASTM E413 standards.*

(4) AIIC (FIIC): Field Impact Insulation Class. Tests in compliance with the ASTM E007-11 and ASTM E989-11 standards.*

*ASTC and AIIC results are presented for information purposes only. Equivalent performance cannot be guaranteed by SOPREMA and RESISTO.