

## PRODUCT DATA SHEET

### DESCRIPTION & FEATURES

ELASTOPHENE FR GR (fire retardant, granulated) is an SBS-modified bitumen cap ply for use in approved multi-ply membrane and flashing assemblies. ELASTOPHENE FR GR is composed of a proprietary formulation of elastomeric styrene-butadiene-styrene (SBS) polymer modified bitumen and is reinforced with a high quality random glass fiber mat. The topside is surfaced with ceramic coated granules and the underside is surfaced with fine mineral aggregate to facilitate cold adhesive application.

*ELASTOPHENE FR GR includes the standard white granules. Contact SOPREMA® Customer Service or your sales representative for other granule color options and special order requirements.*

### STORAGE & HANDLING

Store rolls on end and maintain in an upright position to prevent damage. Store rolls in a clean dry location and cover as necessary to protect rolls from environmental damage such as extreme cold, heat, or moisture. Monitor varying environmental conditions during storage, handling and application of ELASTOPHENE FR GR.

### APPLICATION

Prior to installation, unroll ELASTOPHENE FR GR onto the roof surface and allow to relax. Place ELASTOPHENE FR GR in desired position and back roll the product. Apply approved cold adhesive following manufacturer specifications. ELASTOPHENE FR GR is then rolled into the cold adhesive and subsequently broomed in. Refer to the SOPREMA SBS Roofing Installation Guide for additional application guidelines.



APPLICATION



COLD ADHESIVE

### COOL ROOF RATING

PRODUCT	SOLAR REFLECTANCE		THERMAL EMITTANCE		SRI	
	initial	3 year	initial	3 year	initial	3 year
ELASTOPHENE FR GR Standard white granules (WH)	0.27	0.25	0.87	0.89	27	25
ELASTOPHENE FR GR Highly reflective white granules (SG)	0.70	0.62*	0.90	0.90*	86	75*
ELASTOPHENE FR GR Smog reducing granules (ECO3)**	0.10	pending	0.89	pending	6	pending

\*CRRC Rapid Ratings. Refer to Cool Roof Ratings Council (CRRC).

\*\*Calculated using internal testing

QUICK FACTS

ASTM STANDARD	LENGTH (ft)	WIDTH (in)	COVERAGE* (ft <sup>2</sup> )	THICKNESS (mils)	ROLL WEIGHT (lb)	ROLLS/PALLET (pallet weight)
D6163 Type 1, Grade G	32.8 (10.0 m)	39.4 (1.0 m)	97.9 (9.1 m <sup>2</sup> )	140 (3.5 mm)	107 (48.5 kg)	30 (3,260 lb/ 1,479 kg)

\* Coverage rate as reported assumes installation using side and end lap recommendations.



**SOPREMA®**

[www.soprema.us](http://www.soprema.us)  
 310 Quadral Drive, Wadsworth, Ohio 44281  
 Toll Free: (800) 356-3521 | Tel: (330) 334-0066

TECHNICAL INFORMATION & TESTING

SHEET PROPERTIES	
Reinforcement	Glass fiber
Elastomeric bitumen	Proprietary blend of bitumen and SBS polymers
Top surfacing	Ceramic coated granules
Back surfacing	Sanded
Selvage surface	Sanded
Selvage width, in (mm)	3 (76)
End lap, in (mm)	6 (152)

DIMENSIONS & MASS		
PROPERTY		TEST METHOD
Thickness, mils (mm)	140 (3.5)	ASTM D5147
Thickness @ selvage, mils (mm)	110 (2.8)	ASTM D5147
Net mass per unit area, lb/100 ft <sup>2</sup> (g/m <sup>2</sup> )	99.4 (4853)	ASTM D5147

PHYSICAL PROPERTIES			
PROPERTY	MD	XMD	TEST METHOD
Peak load @ 0°F (-18°C), lbf/in (kN/m)	110 (19.3)	95 (16.6)	ASTM D5147
Elongation at peak load @ 0°F (-18°C), %	4	4	ASTM D5147
Peak load @ 73.4°F (23°C), lbf/in (kN/m)	50 (8.8)	40 (7.0)	ASTM D5147
Elongation at peak load @ 73.4°F (23°C), %	5	4	ASTM D5147
Ultimate elongation @ 73.4°F (23°C), %	50	50	ASTM D5147
Tear strength @ 73.4°F (23°C), lbf (N)	60 (267)	60 (267)	ASTM D5147
Low temperature flexibility, °F (°C)	-15 (-26)	-15 (-26)	ASTM D5147
Dimensional stability, %	< 0.1	< 0.1	ASTM D5147
Compound stability, °F (°C)	250 (121)	250 (121)	ASTM D5147
Granule embedment, g	< 1.5 avg; 2.0 max for SG		ASTM D5147
Cyclic fatigue, condition 4	Pass		ASTM D5849

\* Data is represented by average values, unless noted otherwise.

TESTING & APPROVALS

