

# ALSAN® RS

## METAL PRIMER

ALSAN® RS METAL PRIMER  
PRODUCT # L-RS1MP

## PRODUCT DATA SHEET

### DESCRIPTION & FEATURES

ALSAN RS Metal Primer is an acrylic primer used with various metal substrates to promote adhesion of ALSAN RS roofing, waterproofing and surfacing components. ALSAN RS Metal Primer is recommended for all metal tie-ins and required for applications with higher mechanical stresses, on detail work with small contact areas, metal drain bowls, metal components with large linear thermal expansion or edge metal terminations.

### STORAGE

Always store closed containers in cool, ventilated and dry locations away from heat and oxidizing agents. Do not store in direct sunlight or in temperatures below 50°F (10°C) or above 90°F (32°C). Do not allow to freeze. Approximate shelf life is twelve months from date of shipment when properly stored sealed and unmixed.

### APPLICATION

Apply ALSAN RS Metal Primer to clean prepared metals using a brush or roller. Prior to application, refer to published specifications, guidelines and recommendations for complete application instructions. The applicator is responsible for ensuring conditions are appropriate to proceed with proper application methods.

APPLICATION



BRUSH



ROLLER

QUICK FACTS

UNIT SIZE (gal)	COVERAGE (ft <sup>2</sup> )	AMBIENT TEMP (°F)	SUBSTRATE TEMP (°F)	RAIN PROOF (hours)	NEXT LAYER (hours)	FULLY CURED (hours)
1 (3.8 L)	250 (23.2 m <sup>2</sup> )	50-95 (10 to 35°C)	50-95 (10 to 35°C)	4 at 68°F (20°C)	6 at 68°F (20°C)	24 at 68°F (20°C)



**SOPREMA®**

[www.soprema.us](http://www.soprema.us)  
310 Quadral Drive, Wadsworth, Ohio 44281  
Toll Free: (800) 356-3521 | Tel: (330) 334-0066

TECHNICAL INFORMATION & TESTING

**APPROXIMATE COVERAGE RATES**

SUBSTRATE PROFILE	MINIMUM TOTAL COVERAGE gal/100 ft <sup>2</sup> (L/m <sup>2</sup> )	TOTAL DRY THICKNESS mils(mm)
SSPC - SP3	0.4 (0.16)	4 (0.102)

**PHYSICAL PROPERTIES**

DESCRIPTION	PROPERTY	STANDARD
Color	White	ASTM D562
Solids, %	+/- 70	ASTM D1644
Viscosity, stormer type @ 77°F (25°C), KU (cps)	75-85 (720-1,000)	ASTM D562 (Method A)
VOC, g/L	< 50	EPA Method 24

\* Data is represented by average values, unless noted otherwise.