

# SENTINEL®

## P200 HFB

SENTINEL® P200 HFB  
 PRODUCT #  
 P305 (White)  
 P305-T (Tan)  
 P305-G (Grey)

## PRODUCT DATA SHEET

### DESCRIPTION & FEATURES

SENTINEL P200 HFB is a high performance, polyester reinforced, thermoplastic polyvinyl chloride (PVC) roof membrane, specially designed to provide unmatched flexibility and long-term performance. SENTINEL membranes provide the proven fire and chemical resistance of PVC along with superior weldability, making it easy to conform to complex geometries. SENTINEL P200 HFB incorporates a heavy fleece-backed underside and is available in an ENERGY STAR® approved white as well as a variety of colors, including gray and tan.

### STORAGE

Store rolls in a clean, dry location and cover as necessary to protect rolls from environmental damage such as extreme cold, heat, or moisture. Monitor varying environmental conditions during storage, handling and application of SENTINEL P200 HFB.

### APPLICATION

SENTINEL P200 HFB can be installed in mechanically attached or fully adhered systems. For fully adhered systems, SENTINEL H2O Bonding Adhesive or DUOTACK SPF are approved. Please refer to the specific adhesive data sheet for application guidelines. For mechanically attached systems, please consult your SOPREMA representative for specific fastening patterns. All laps must be heat-welded to ensure a water tight seal.

### COOL ROOF RATING

PRODUCT	SOLAR REFLECTANCE		THERMAL EMITTANCE		SRI	
	Initial	3 year	Initial	3 year	Initial	3 year
SENTINEL P200 HFB	0.85	0.73	0.89	0.88	108	0.90
SENTINEL P200 HFB Light Grey	0.46	pending 3 year	0.89	pending 3 year	53	pending 3 year
SENTINEL P200 HFB Light Tan	0.72	pending 3 year	0.85	pending 3 yaer	88	pending 3 year

APPLICATION



MECHANICALLY FASTENED



FULLY ADHERED

QUICK FACTS

ROLL WIDTH (ft)	ROLL LENGTH (ft)	COVERAGE (ft²)	THICKNESS (mils)	ROLL WEIGHT (lb)	ROLLS/PALLET (pallet weight)
10 (3.0 m)	65 (19.8 m)	650 (60.4 m²)	80 (2.0 mm)	354 (160.6 kg)	10 (3,690 lb/ 1,674 kg)

\* Coverage rate as reported assumes installation using side and end lap recommendations.



**SOPREMA®**

[www.soprema.us](http://www.soprema.us)  
 310 Quadral Drive, Wadsworth, Ohio 44281  
 Toll Free: (800) 356-3521 | Tel: (330) 334-0066

## TECHNICAL INFORMATION & TESTING

### SHEET PROPERTIES

Reinforcement	Polyester (18X9, weft inserted)
Back surfacing	Heavy fleece-backed (5.5 oz/yd <sup>2</sup> )
ATSM Type	ATSM D4434, Type III

### DIMENSIONS & MASS

PROPERTY		TEST METHOD
Thickness, mils (mm) (without fleece backing)	80 (2.0)	ASTM D4434
Thickness over scrim, mils (mm)	40 (1.02)	ASTM D4434
Net mass per unit area, lb/100ft <sup>2</sup> (g/m <sup>2</sup> )	49 (2,368)	ASTM D4434

### PHYSICAL PROPERTIES

PROPERTY	MD	XMD	TEST METHOD
Breaking strength, lbf/in (kN/m)	500 (88)	350 (61)	ASTM D751
Elongation at break, minimum, %	30	30	ASTM D751
Seam strength (minimum 75% of breaking strength)	Pass	Pass	ASTM D751
Tearing strength, lbf (N)	115 (512)	65 (289)	ASTM D751, PROC B
Trapezoidal Tear, lbf (N)	185 (823)	155 (689)	ATSM D751
Low temperature bend, @ -40°F (-40°C)	Pass	Pass	ASTM D2136
Linear dimensional change, %	< 0.1	< 0.1	ASTM D1204
Change in weight after immersion in water, %	< 3	< 3	ASTM D570
Static puncture resistance, @ ≥ 33 lbf (15 kg), minimum	Pass	Pass	ASTM D5602
Dynamic puncture resistance, @ 20 J, minimum	Pass	Pass	ASTM D5635

\* Data is represented by average values, unless noted otherwise.

## TESTING & APPROVALS

