

ALSAN[®] RS

263 LO SELF-LEVELING MORTAR

ALSAN[®] RS 263
SELF-LEVELING MORTAR

PRODUCT COMPONENTS:
ALSAN RS 240 LO - L-RS015S
ALSAN RS 223 POWDER - L-RS223

PRODUCT DATA SHEET

DESCRIPTION & FEATURES

ALSAN RS 263 LO Self-Leveling Mortar is created by combining ALSAN RS 240 LO and ALSAN RS 223 Mixing Powder. ALSAN RS 263 LO Self-Leveling Mortar is a trowel applied low odor resin-mortar used as a thick coating system for interior and exterior unreinforced waterproofing and surfacing applications. ALSAN RS 263 LO Self-Leveling Mortar is also used as a traffic surfacing applied over ALSAN RS reinforced waterproofing membranes.

STORAGE

Always store closed containers in cool, ventilated and dry locations away from heat and oxidizing agents. Do not store in direct sunlight or in temperatures below 32°F (0°C) or above 77°F (25°C). Approximate shelf life is twelve months from date of manufacture when properly stored sealed and unmixed.

APPLICATION

Thoroughly mix the entire drum of ALSAN RS 240 LO and ALSAN RS 223 Mixing Powder before pouring off, batch mixing or catalyzing. Apply ALSAN RS 263 Self-Leveling Mortar using a notched trowel and pin roller. The applicator is responsible for ensuring conditions are appropriate to proceed with proper application methods.

Refer to ALSAN RS 240 LO and ALSAN RS 223 Mixing Powder product data sheets for additional information.



APPLICATION



ROLLER



TROWEL

QUICK FACTS

UNIT SIZE (kg)	AMBIENT TEMP (°F)	SUBSTRATE TEMP (°F)	RESIN TEMP (°F)	POT LIFE (min)	RAIN PROOF (min)	NEXT LAYER (min)	FULLY CURED (hour)
33 (17.8 L)	37-95 (3-35°C)	37-122 (3-50°C)	37-86 (3-30°C)	15-20 (at 68°F (20°C))	45-60 (at 68°F (20°C))	120 (at 68°F (20°C))	5 (at 68°F (20°C))



SOPREMA[®]

www.soprema.us
310 Quadral Drive, Wadsworth, Ohio 44281
Toll Free: (800) 356-3521 | Tel: (330) 334-0066

TECHNICAL INFORMATION & TESTING

ALSAN RS 263 LO Self-Leveling Mortar requires combining one drum of ALSAN RS 240 LO (10 kg) with one bag of ALSAN RS 223 Mixing Powder (23 kg) creating a 33 kg work pack. The mixing ratio is 1 to 2.3 resin to powder respectively.

APPROXIMATE COVERAGE RATES

SUBSTRATE PROFILE	MINIMUM TOTAL CONSUMPTION kg/ft ² (kg/m ²)	TOTAL THICKNESS mils(mm)
Smooth to CSP-3	0.37 (4.0)	88 (2.2)

CATALYST MIXING CHART

CATALYST REQUIRED	6% Catalyst 32°F (0°C) to 50°F (10°C)		4% Catalyst 50°F (10°C) to 68°F (20°C)		2% Catalyst 68°F (20°C) to 95°F (35°C)	
33 kg work pack	6 0.1 kg packets		4 0.1 kg packets		2 0.1 kg packets	
1 kg (ALSAN RS 263 LO SELF LEVELING MORTAR)	TBSP	kg	TBSP	kg	TBSP	kg
	2	0.18	1	0.01	0.5	0.006
1 liter (~1.85 kg) (ALSAN RS 263 LO SELF LEVELING MORTAR)	3	0.33	2	0.02	1	0.01

PHYSICAL PROPERTIES

PROPERTY	TEST METHOD
Mix density @ 73.4°F (23°C), lb/gal (g/ml)	15.4 (1.85) ASTM D51475
Viscosity, stormer type @ 77°F (25°C), KU (cps)	90 (1100) ASTM D562 (Method A)
Indentation hardness @ 73.4°F (23°C), Shore A	85 ASTM D2240
Abrasion resistance, 4" disc, lb (mg)	0.00043 (194) ASTM D4060

* All data is represented by averages, unless noted otherwise.