

INSONO

AF3 PRIMER

PRODUCT DATA SHEET

DESCRIPTION & FEATURES

INSONO AF3 Primer is a water-based polymer emulsion primer. INSONO AF3 Primer is designed to improve the adhesion of INSONO AF3 self-adhered soundproofing membranes on most substrates when the use of solvent-based primers is not advised. The recommended substrates are concrete, plywood and gypsum boards.

STORAGE

Store the product in a well-ventilated area, away from freezing conditions, moisture, heat and direct sunlight. Product can be stored for up to 24 months in original sealed container.

APPLICATION

Surface must be dry, clean and free of oil, grease, dirt or debris. INSONO AF3 Primer is applied via paint brush or roller. Apply the primer layer at a rate of 0.5 gal/100 ft² (0.2 L/m²) with a thickness of 8 mils. Coverage rate may vary depending on the substrate. Allow INSONO AF3 Primer to dry 20 to 30 minutes prior to membrane application. Membranes must be installed on the same day as the INSONO AF3 Primer application. Drying time varies depending on surface and on environmental factors including relative humidity, wind, ambient temperature and other factors. Minimum application temperature is 25°F (-4°C). Do not dilute INSONO AF3 Primer with water.

APPLICATION



BRUSH



ROLLER

QUICK FACTS

PACKAGING (Gal)	PACKAGING (Gal)	COVERAGE 1 Gal Container (ft ²)	COVERAGE 5 Gal Container (ft ²)
1 (3.78 L)	5 (19 L)	129 - 409 (12 - 38 m ²)	650 - 2000 (60 - 190 m ²)



SOPREMA[®]

www.soprema.us
310 Quadral Drive, Wadsworth, Ohio 44281
Toll Free: (800) 356-3521 | Tel: (330) 334-0066

TECHNICAL INFORMATION & TESTING

PROPERTIES	
Packaging, Gal (L)	1 (3.78) or 5 (19)
Application rate, ft ² (m ²)	1 Gallon (3.78 L) 129 to 409 (12 to 38)
Application rate, ft ² (m ²)	5 Gallon (19 L) 650 to 2000 (60 to 190)
Drying time	20 to 30 minutes, depending on temperature and quantity applied. Must be dried when touched
Physical state	Liquid
Color	Light blue
Specific gravity at 68°F (20°C)	1.01 kg/L
Solida by weight	28%
Brookfield viscosity, 77°F (25°C)	400eP