

ELASTOPHENE®

FLAM LS FR GR

ELASTOPHENE® FLAM
LS FR GR
PRODUCT # 01264 (WH)
05004 (SG)

PRODUCT DATA SHEET

DESCRIPTION & FEATURES

ELASTOPHENE Flam LS FR GR (low slope, fire retardant, granulated) is an SBS-modified bitumen cap ply for use in approved multi-ply membrane and flashing assemblies. ELASTOPHENE Flam LS FR GR is composed of a proprietary formulation of elastomeric styrene-butadiene-styrene (SBS) polymer modified bitumen and is reinforced with a high quality random glass fiber mat. The topside is surfaced with ceramic coated granules and underside is surfaced with polyolefin burn-off film to optimize heat welding.

ELASTOPHENE Flam LS FR GR includes the standard white granules. Contact SOPREMA® Customer Service or your sales representative for other granule color options and special order requirements.

STORAGE & HANDLING

Store rolls on end and maintain in an upright position to prevent damage. Store rolls in a clean dry location and cover as necessary to protect rolls from environmental damage such as extreme cold, heat, or moisture. Monitor varying environmental conditions during storage, handling and application of ELASTOPHENE Flam LS FR GR.

APPLICATION

Prior to installation, unroll ELASTOPHENE Flam LS FR GR onto the roof surface and allow to relax. Position ELASTOPHENE Flam FR GR in desired position and back roll the product. ELASTOPHENE Flam FR GR is then heat welded to approved substrates. Refer to the SOPREMA® SBS Roofing Guide for additional application guidelines.



APPLICATION



HEAT-WELDED

COOL ROOF RATING

PRODUCT	SOLAR REFLECTANCE		THERMAL EMITTANCE		SRI	
	initial	3 year	initial	3 year	initial	3 year
ELASTOPHENE Flam LS FR GR (WH) Standard white granules	0.27	0.25	0.87	0.89	27	25
ELASTOPHENE Flam LS FR GR (SG) Highly reflective white granules	0.70	0.62*	0.90	0.90*	86	75

* CRRC Rapid Ratings. Refer to Cool Roof Ratings Council (CRRC).

QUICK FACTS

ASTM STANDARD	LENGTH (ft)	WIDTH (in)	COVERAGE* (ft²)	THICKNESS (mils)	ROLL WEIGHT (lb)	ROLLS/PALLET (pallet weight)
D6163 Type 1, Grade G	32.8 (10.0 m)	39.4 (1.0 m)	97.9 (9.1 m²)	140 (3.5 mm)	106 (48.1 kg)	25 (2,700 lb/ 1,245 kg)

* Coverage rate as reported assumes installation using side and end lap recommendations.



SOPREMA®

www.soprema.us
310 Quadral Drive, Wadsworth, Ohio 44281
Toll Free: (800) 356-3521 | Tel: (330) 334-0066

TECHNICAL INFORMATION & TESTING

SHEET PROPERTIES	
Reinforcement	Glass fiber
Elastomeric bitumen	Proprietary blend of bitumen and SBS polymers
Top surfacing	Ceramic coated granules
Back surfacing	Polyolefin film
Selvage surface	Polyolefin film
Selvage width, in (mm)	3 (76)
End lap, in (mm)	6 (152)

DIMENSIONS & MASS		
PROPERTY		TEST METHOD
Thickness, mils (mm)	140 (3.5)	ASTM D5147
Thickness @ selvage, mils (mm)	98 (2.5)	ASTM D5147
Net mass per unit area, lb/100 ft ² (g/m ²)	98.5 (4808)	ASTM D5147
Bottom coating thickness, mils (mm)	≥ 40 (1.0)	ASTM D5147

PHYSICAL PROPERTIES			
PROPERTY	MD	XMD	TEST METHOD
Peak load @ 0°F (-18°C), lbf/in (kN/m)	110 (19.3)	95 (16.6)	ASTM D5147
Elongation at peak load @ 0°F (-18°C), %	4	4	ASTM D5147
Peak load @ 73.4°F (23°C), lbf/in (kN/m)	50 (8.8)	40 (7.0)	ASTM D5147
Elongation at peak load @ 73.4°F (23°C), %	5	4	ASTM D5147
Ultimate elongation @ 73.4°F (23°C), %	50	50	ASTM D5147
Tear strength @ 73.4°F (23°C), lbf (N)	60 (267)	60 (267)	ASTM D5147
Low temperature flexibility, °F (°C)	-15 (-26)	-15 (-26)	ASTM D5147
Dimensional stability, %	< 0.1	< 0.1	ASTM D5147
Compound stability, °F (°C)	250 (121)	250 (121)	ASTM D5147
Granule embedment, g	< 1.5 avg; 2.0 max for SG		ASTM D5147

* Data is represented by average values, unless noted otherwise.

TESTING & APPROVALS



FLORIDA BUILDING CODE

MIAMI-DADE COUNTY APPROVED

