

PRODUCT DATA SHEET

DESCRIPTION & FEATURES

SOPRAPHIX Base 622 is an SBS-modified bitumen base ply for use in approved multi-ply membrane and flashing assemblies and is designed specifically for mechanical attachment to approved substrates. SOPRAPHIX Base 622 is composed of a proprietary formulation of elastomeric styrene-butadiene-styrene (SBS) polymer modified bitumen and is reinforced with a tough, dimensionally stable non-woven polyester mat engineered for mechanical attachment. The topside and underside are surfaced with fine mineral aggregate to facilitate subsequent cold adhesive or self adhered application.

STORAGE & HANDLING

Store rolls on end and maintain in an upright position to prevent damage. Store rolls in a clean dry location and cover as necessary to protect rolls from environmental damage such as extreme cold, heat, or moisture. Monitor varying environmental conditions during storage, handling and application of SOPRAPHIX Base 622.

APPLICATION

Prior to installation, unroll SOPRAPHIX Base 622 onto the roof surface and allow to relax. Place SOPRAPHIX Base 622 in desired position. SOPRAPHIX Base 622 is mechanically fastened through the 4 inch or 5 inch side laps using the 2 inch or 2.4 inch plates respectively following the details for the required uplift pressure. Subsequent approved inter-ply or cap ply membranes are applied to SOPRAPHIX Base 622 via cold adhesive or self adhered. Refer to the SOPREMA® SBS Roofing Manual for additional application guidelines.



APPLICATION



MECHANICALLY
FASTENED

QUICK FACTS

ASTM STANDARD	LENGTH (ft)	WIDTH (in)	COVERAGE* (ft ²)	THICKNESS (mils)	ROLL WEIGHT (lb)	ROLLS/PALLET (pallet weight)
D6164 Type 1, Grade S	32.8 (10.0 m)	39.4 (1.0 m)	4- 95.2 (8.8 m ²) 5- 92.5 (8.6 m ²)	110 (2.8 mm)	74 (33.6 kg)	30 (2,270 lb/ 1,030 kg)

* Coverage rate as reported assumes installation using side and end lap recommendations. Coverage reported reflects 4 and 5 inch side laps respectively.



SOPREMA®

www.soprema.us
310 Quadral Drive, Wadsworth, Ohio 44281
Toll Free: (800) 356-3521 | Tel: (330) 334-0066

TECHNICAL INFORMATION & TESTING

SHEET PROPERTIES	
Reinforcement	Non-woven polyester
Elastomeric bitumen	Proprietary blend of bitumen and SBS polymers
Top surfacing	Sanded
Back surfacing	Sanded
Selvage width, in (mm)	4 (102) and 5 (127)
End lap, in (mm)	6 (152)

DIMENSIONS & MASS		
PROPERTY		TEST METHOD
Thickness, mils (mm)	110 (2.8)	ASTM D5147
Net mass per unit area, lb/100ft ² (g/m ²)	68 (3341)	ASTM D5147

PHYSICAL PROPERTIES			
PROPERTY	MD	XMD	TEST METHOD
Peak load @ 0°F (-18°C), lbf/in (kN/m)	115 (20.1)	90 (15.8)	ASTM D5147
Elongation at peak load @ 0°F (-18°C), %	35	40	ASTM D5147
Peak load @ 73.4°F (23°C), lbf/in (kN/m)	85 (14.9)	65 (11.4)	ASTM D5147
Elongation at peak load @ 73.4°F (23°C), %	55	60	ASTM D5147
Ultimate elongation @ 73.4°F (23°C), %	65	80	ASTM D5147
Tear strength @ 73.4°F (23°C), lbf (N)	125 (556)	85 (378)	ASTM D5147
Low temperature flexibility, °F (°C)	-15 (-26)	-15 (-26)	ASTM D5147
Dimensional stability, %	< 0.5	< 0.5	ASTM D5147
Compound stability, °F (°C)	240 (116)	240 (116)	ASTM D5147

* Data is represented by average values, unless noted otherwise.

TESTING & APPROVALS

