

# ELASTOPHENE®

## STICK FR GR

ELASTOPHENE®  
STICK FR GR  
PRODUCT # 05012

## PRODUCT DATA SHEET

### DESCRIPTION & FEATURES


ELASTOPHENE Stick FR GR (granules) is an SBS-modified bitumen cap ply for use in approved multi-ply membrane and flashing assemblies. ELASTOPHENE Stick FR GR is composed of a proprietary formulation of elastomeric styrene-butadiene-styrene (SBS) polymer modified bitumen and is reinforced with a tough, high quality random glass fiber mat. The topside is surfaced with ceramic coated granules and underside is surfaced with a protective polyolefin release film that is removed during application.

### STORAGE & HANDLING

Store rolls on end and maintain in an upright position to prevent damage. Store rolls in a clean dry location and cover as necessary to protect rolls from environmental damage such as extreme cold, heat, or moisture. Monitor varying environmental conditions during storage, handling and application of ELASTOPHENE Stick FR GR.

### APPLICATION

Prior to installation, unroll ELASTOPHENE Stick FR GR onto the roof surface and allow to relax. Place ELASTOPHENE Stick FR GR in desired position. Remove the protective release film from the underside of the sheet and roll ELASTOPHENE Stick FR GR into place with a weighted roller. Refer to the SOPREMA SBS Roofing Manual for additional application guidelines.



APPLICATION



SELF-ADHERED

### COOL ROOF RATING

PRODUCT	SOLAR REFLECTANCE		THERMAL EMITTANCE		SRI	
	initial	3 year	initial	3 year	initial	3 year
ELASTOPHENE Stick FR GR (WH) Standard white granules	0.27	0.25	0.87	0.89	27	25
ELASTOPHENE Stick FR GR (SG) Highly reflective white granules	0.70	0.62*	0.90	0.90*	86	75

\* CRRC Rapid Ratings. Refer to Cool Roof Ratings Council (CRRC).

QUICK FACTS

ASTM STANDARD	LENGTH (ft)	WIDTH (in)	COVERAGE* (ft²)	THICKNESS (mils)	ROLL WEIGHT (lb)	ROLLS/PALLET (pallet weight)
D6163 Type 1, Grade G	32.8 (10.0 m)	39.4 (1.0 m)	97.9 (9.1 m²)	142 (3.6 mm)	93 (42.2 kg)	25 (2375 lb/ 1077 kg)

\* Coverage rate as reported assumes installation using side and end lap recommendations.



**SOPREMA®**

[www.soprema.us](http://www.soprema.us)  
310 Quadral Drive, Wadsworth, Ohio 44281  
Toll Free: (800) 356-3521 | Tel: (330) 334-0066

## TECHNICAL INFORMATION & TESTING

SHEET PROPERTIES	
Reinforcement	Glass fiber
Elastomeric bitumen	Proprietary blend of bitumen and SBS polymers
Top surfacing	Ceramic coated granules
Back surfacing	Self-adhered with release film
Selvage surface	Self-adhered with release film
Selvage width, in (mm)	3 (76)
End lap, in (mm)	6 (152)

DIMENSIONS & MASS		
PROPERTY		TEST METHOD
Thickness, mils (mm)	142 (3.6)	ASTM D5147
Thickness @ selvage, mils (mm)	102 (2.6)	ASTM D5147
Net mass per unit area, lb/100ft <sup>2</sup> (g/m <sup>2</sup> )	86.4 (4218)	ASTM D5147

PHYSICAL PROPERTIES			
PROPERTY	MD	XMD	TEST METHOD
Peak load @ 0°F (-18°C), lbf/in (kN/m)	110 (19.3)	95 (16.6)	ASTM D5147
Elongation at peak load @ 0°F (-18°C), %	4	4	ASTM D5147
Peak load @ 73.4°F (23°C), lbf/in (kN/m)	50 (8.8)	40 (7.0)	ASTM D5147
Elongation at peak load @ 73.4°F (23°C), %	5	4	ASTM D5147
Ultimate elongation @ 73.4°F (23°C), %	50	50	ASTM D5147
Tear strength @ 73.4°F (23°C), lbf (N)	60 (267)	60 (267)	ASTM D5147
Low temperature flexibility, °F (°C)	-15 (-26)	-15 (-26)	ASTM D5147
Dimensional stability, %	< 0.1	< 0.1	ASTM D5147
Compound stability, °F (°C)	250 (121)	250 (121)	ASTM D5147
Granule embedment, g	< 1.5 avg; 2.0 max for SG		ASTM D5147

\* Data is represented by average values, unless noted otherwise.

## TESTING & APPROVALS



FLORIDA BUILDING CODE

