

ELASTOPHENE®

FLAM STICK

ELASTOPHENE®
FLAM STICK
PRODUCT # 00570

PRODUCT DATA SHEET

DESCRIPTION & FEATURES

ELASTOPHENE Flam Stick is an SBS-modified bitumen, self-adhered base ply for use in approved multi-ply membrane and flashing assemblies. ELASTOPHENE Flam Stick is composed of a proprietary formulation of elastomeric styrene-butadiene-styrene (SBS) polymer modified bitumen in combination with a high tack self-adhesive layer and is reinforced with a high quality random glass fiber mat. The topside is surfaced with polyolefin burn-off film to optimize heat welding and the underside is surfaced with protective polyolefin release film that is removed during application.

STORAGE & HANDLING

Store rolls on end and maintain in an upright position to prevent damage. Store rolls in a clean dry location and cover as necessary to protect rolls from environmental damage such as extreme cold, heat, or moisture. Monitor varying environmental conditions during storage, handling and application of ELASTOPHENE Flam Stick.

APPLICATION

Prior to installation, unroll ELASTOPHENE Flam Stick onto the roof surface and allow to relax. Place ELASTOPHENE Flam Stick in desired position. Remove the protective release film from the underside of the sheet and roll ELASTOPHENE Flam Stick into place with a weighted roller. Subsequent approved inter-ply or cap ply membranes are applied to ELASTOPHENE Flam Stick via heat welding. Refer to the SOPREMA SBS Roofing Manual for additional application guidelines.



APPLICATION



SELF-ADHERED

QUICK FACTS

ASTM STANDARD	LENGTH (ft)	WIDTH (in)	COVERAGE* (ft ²)	THICKNESS (mils)	ROLL WEIGHT (lb)	ROLLS/PALLET (pallet weight)
D6163 Type 1, Grade S	49.2 (15.0 m)	39.4 (1.0 m)	147.6 (13.7 m ²)	87 (2.2 mm)	75 (33.9 kg)	30 (2300 lb/ 1043 kg)

* Coverage rate as reported assumes installation using side and end lap recommendations.



SOPREMA®

www.soprema.us

310 Quadral Drive, Wadsworth, Ohio 44281
Toll Free: (800) 356-3521 | Tel: (330) 334-0066

TECHNICAL INFORMATION & TESTING

SHEET PROPERTIES	
Reinforcement	Glass fiber
Elastomeric bitumen	Proprietary blend of bitumen and SBS polymers
Top surfacing	Polyolefin film
Back surfacing	Self-adhesive with release film
Selvage surface	Self-adhesive with release film
Selvage width, in (mm)	3 (76)
End lap, in (mm)	6 (152)

DIMENSIONS & MASS		
PROPERTY		TEST METHOD
Thickness, mils (mm)	87 (2.2)	ASTM D5147
Net mass per unit area, lb/100ft ² (g/m ²)	46 (2257)	ASTM D5147

PHYSICAL PROPERTIES			
PROPERTY	MD	XMD	TEST METHOD
Peak load @ 0°F (-18°C), lbf/in (kN/m)	100 (17.6)	90 (15.8)	ASTM D5147
Elongation at peak load @ 0°F (-18°C), %	4	4	ASTM D5147
Peak load @ 73.4°F (23°C), lbf/in (kN/m)	50 (8.8)	40 (7.0)	ASTM D5147
Elongation at peak load @ 73.4°F (23°C), %	5	4	ASTM D5147
Ultimate elongation @ 73.4°F (23°C), %	45	45	ASTM D5147
Tear strength @ 73.4°F (23°C), lbf (N)	60 (267)	60 (267)	ASTM D5147
Low temperature flexibility, °F (°C)	-15 (-26)	-15 (-26)	ASTM D5147
Dimensional stability, %	< 0.1	< 0.1	ASTM D5147
Compound stability, °F (°C)	250 (121)	250 (121)	ASTM D5147

* Data is represented by average values, unless noted otherwise.

TESTING & APPROVALS



FLORIDA BUILDING CODE

