

# ALSAN® RS

## TEXTURED COATING

ALSAN® RS  
TEXTURED COATING  
PRODUCT # L-RSTXTCTG  
(pebble grey)

## PRODUCT DATA SHEET

### DESCRIPTION & FEATURES

ALSAN RS Textured Coating is a rapid-setting, proprietary formulation polymethyl methacrylate (PMMA) liquid resin with integrally mixed aggregate. ALSAN RS Textured Coating is used primarily with vehicular traffic installations at ramps, turning radii and areas of heavy use like roof walkway areas.

### STORAGE

Always store closed containers in a cool, ventilated and dry location away from heat and oxidizing agents. Do not store in direct sunlight or in temperatures below 32°F (0°C) or above 77°F (25°C). Approximate shelf life is twelve months from date of shipment when properly stored, sealed and unmixed.

### APPLICATION

Apply ALSAN RS Textured Coating with a roller and trowel. The applicator is responsible for ensuring conditions are appropriate to proceed with proper application methods.



APPLICATION



TROWEL



ROLLER

QUICK FACTS

UNIT SIZE (kg)	AMBIENT TEMP (F°)	SUBSTRATE TEMP (F°)	RESIIN TEMP (F°)	POT LIFE (min)	RAIN PROOF (min)	NEXT LAYER (min)	FULLY CURED (hour)
15 (8.1 L)	32-95 (0-35°C)	32-122 (0-50°C)	37-86 (3 to 30°C)	10-15 at 68°F (20°C)	30 at 68°F (20°C)	45 at 68°F (20°C)	2 at 68°F (20°C)



**SOPREMA®**

[www.soprema.us](http://www.soprema.us)  
310 Quadral Drive, Wadsworth, Ohio 44281  
Toll Free: (800) 356-3521 | Tel: (330) 334-0066

## TECHNICAL INFORMATION & TESTING

### APPROXIMATE COVERAGE RATES

SUBSTRATE PROFILE	15 KG UNIT ft <sup>2</sup> (m <sup>2</sup> )	MINIMUM TOTAL kg/ft <sup>2</sup> (kg/m <sup>2</sup> )	TOTAL THICKNESS mils(mm)
<b>Standard duty</b>	46 (4.3)	0.33 (3.5)	76 (1.89)

Catalyst quality will range from 2-6% (by weight) dependent on the ambient temperature.

### CATALYST MIXING CHART

CATALYST REQUIRED	6% Catalyst 32°F (0°C) to 50°F (10°C)		4% Catalyst 50°F (10°C) to 68°F (20°C)		2% Catalyst 68°F (20°C) to 95°F (35°C)	
	TBSP	kg	TBSP	kg	TBSP	kg
15 kg can	<b>9</b> 0.1 kg packets		<b>6</b> 0.1 kg packets		<b>3</b> 0.1 kg packets	
1 kg	6	0.06	4	0.04	2	0.02
1 liter (~1.85 kg)	11	0.11	7	0.07	3.5	0.037

\* Data is represented by average values, unless noted otherwise.

## TESTING & APPROVALS

FLORIDA BUILDING CODE