

SOPRA-XPS 35



APPLICATIONS

ROOFING

PRODUCT DATA SHEET PD10437-REV.001821

DESCRIPTION:

SOPRA-XPS 35 is a rigid thermal insulation board made of closed cell extruded polystyrene with shiplap or square edges on its four sides. The optimized formula of **SOPRA-XPS 35** contains no CFC, no HCFC and no HFC 134a. Moreover, this formula has zero ozone depletion potential and a very low global warming potential (less than 50). **SOPRA-XPS 35** has low VOC emissions, it has been tested and determined compliant in accordance with California Department of Public Health (CDPH) VI.2 (January 2017).

SOPRA-XPS 35 meets GREENGUARD GOLD certification.

BASIC USES:

It is mainly used as a thermal insulation for **SOPREMA** protected-membrane roofing systems (inverted roofs).

FEATURES AND BENEFITS:

- Stable LTTR (Long Term Thermal Resistance) of 5/inch, even at low temperatures
- Outstanding resistance to moisture
- Eco friendly formula utilizing up to 70% recycled content
- Mold and bacteria resistant

CONFIGURATION:

SOPRA-XPS 35 is available in the following edge treatments :

- Board with squared edges on four sides
- Boards with shiplap edges on four sides

PACKAGING:

Specifications	SOPRA-XPS 35
Available thicknesses* - shiplap boards, in (mm)	1.5 (38) 2 (51) 2.5 (64) 3 (76) 3.5 (89) 4 (102)
Available thicknesses* - square boards, in (mm)	1 (25)
Available board dimensions*, ft (mm)	8 x 2 (2438 x 610)

*Other thicknesses and dimensions available upon request.
(All values are nominal)



SOPRA-XPS 35



APPLICATIONS

ROOFS

INSTALLATION:

LOOSE LAID

- Insulation boards are laid flat on the ground for applications under concrete slab.
- When installing multiple layers of SOPRA-XPS, all joint should be staggered between layers.
- When another layer of SOPRA- XPS 35 insulation is required, it should be installed with staggered joints without being adhered to the first layer.

COLOR:

SOPRA-XPS 35 is grey in color with blue print on the face of the board.

LIMITATION:

- Maximum service temperature: 167 °F (75 °C)
- SOPRA-XPS 35 is installed where the applied loads do not exceed 20 psi
- SOPRA-XPS 35 is a combustible product
- SOPRA-XPS 35 can not be used in a wall assembly with a combustible veneer
- SOPRA-XPS 35 should not be exposed to UV rays for more than 60 days

FOR COMPLETE INFORMATION ON PRODUCT INSTALLATION, PLEASE CONSULT YOUR SOPREMA REPRESENTATIVE.

SHELF LIFE & STORAGE:

SOPRA-XPS 35 thermal insulation boards are covered with a temporary waterproof packaging for handling the panels in the manufacturing plant and during transit.

SOPRA-XPS 35 thermal insulation boards must be stored on a flat substrate in their original packaging. If the products are stored outdoors, cover them with an opaque protective cover if the original packaging is removed so that the boards are always protected from UV and sheltered from inclement weather. As they are flammable, they must be protected and kept away from flames and intense heat sources during transportation, handling, storage, and installation.

APPROVALS



SOPRA-XPS 35




APPLICATIONS

ROOFS

PROPERTIES:

SOPRA-XPS 35 meets the requirements of ASTM C578-14 Type IV (CAN/ULC S701.1 Type 4).

Properties	Standards	SOPRA-XPS 35
Thermal Resistance ¹ (R Value [RSI-Value] / 1 in [25.4 mm] @ 75 °F [24 °C])	ASTM C518	R – 5.0 (RSI- 0.88)
Water Vapour Permeance, perm (Ng/Pa•s•m ²)	ASTM E96	0.9 (52)
Flame spread rating	ASTM E84	> 25 < 500
Dimensional Stability, max %	ASTM D2126	Pass
Flexural Strength, min psi (kPa)	ASTM C203	93 (640)
Water Absorption by volume max, %	ASTM D2842	0.7
Compressive Strength Min, psi (kPa)	ASTM D1621	35 (241)
Limiting Oxygen Index, %	ASTM D2863	24
Global recycled content, % ²	-	70
Shiplap dimensions		

¹ The long-term thermal performance (LTTR) of SOPRA-XPS 35 complies with CAN/ULC S701.1 standard requirement: min. RSI-1.66 (R-9.4) for Type 4 products that are 50 mm (2 in) thick.

Please consult your SOPREMA representative for more information.

² The recycled content varies according to the compression range. The global recycled content is made of one part post- and pre-consumer content validated by CT Consultant, and another part which accounts for the manufacturing process recovery value. The specific details of the products covered by this validation can be found on the Recycled Content Certificate available on our website.