

ELASTOCOL[®] STICK H2O



APPLICATIONS

ROOFING

PRODUCT DATA SHEET PD10134-Rev. 220202

DESCRIPTION:

ELASTOCOL Stick H2O is water based polymer emulsion primer for use in approved multi-ply membrane and flashing assemblies. ELASTOCOL Stick H2O is used to increase adhesion when using self-adhered SBS membranes. ELASTOCOL Stick H2O may be applied to concrete, gypsum, masonry, metal, wood and SOPREMA mineral aggregate surfaced membranes.

STORAGE:

Store in pail and maintain in an upright position to prevent damage. Store in a clean dry location and cover as necessary to protect pails from environmental damage such as extreme cold, heat, or moisture. Monitor varying environmental conditions during storage, handling and application of ELASTOCOL Stick H2O.

APPLICATION:

ELASTOCOL Stick H2O is mixed prior to application. ELASTOCOL Stick H2O is applied to the approved area via brush, roller or spray equipment. ELASTOCOL Stick H2O is applied at a rate of 0.3 – 0.7 gallons per 100 square feet depending on the substrate. Allow ELASTOCOL Stick H2O to dry 1-3 hours prior to membrane application dependent on environmental factors including humidity, wind, ambient temperature and other factors. When the primer is sufficiently dry, it will become tacky, but will not transfer when touched. ELASTOCOL Stick H2O may not be used over asphaltic coverboards and should not be diluted with water. Refer to the SOPREMA SBS Roofing Manual for additional application guidelines.

PRODUCT INFORMATION

Description	Polymer emulsion
Installation	Brush, roller, or spray
Packaging, gal (L)	5 (19.9)
Application rate, ft ² /gal (m ² /L)	140-330 (3.4-8.1) depending on surface and porosity
Drying time @ 72°F 50% RH, minutes	60
VOC Content, g/L	0

