

SENTINEL[®] COPPERART P150 HFB



APPLICATIONS

ROOFING

PRODUCT DATA SHEET PD10186-Rev. 220315

DESCRIPTION:

SENTINEL CopperArt P150 HFB is a high performance, polyester reinforced, thermoplastic polyvinyl chloride (PVC) roof membrane, specially designed to provide unmatched flexibility and long-term performance. SENTINEL membranes provide the proven fire and chemical resistance of PVC along with superior weldability, making it easy to conform to complex geometries. SENTINEL CopperArt P150 HFB is manufactured using a specialized process that allows copper metallic powder to be incorporated into the PVC blend, producing a non-pigmented copper-PVC membrane that will not chalk or fade. SENTINEL CopperArt P150 not only provides the aesthetics of a copper roof, but it will also oxidize gradually, taking on the patina color, just as copper does, when exposed to the elements. SENTINEL CopperArt P150 HFB incorporates a 300 gram fleece backed underside.

STORAGE:

Store rolls in a clean, dry location and cover as necessary to protect rolls from environmental damage such as extreme cold, heat, or moisture. Monitor varying environmental conditions during storage, handling and application or SENTINEL CopperArt P150 HFB.

APPLICATION:

SENTINEL CopperArt P150 HFB may be mechanically fastened or fully adhered. For fully adhered systems, SENTINEL H2O or Duotack SPF Bonding adhesives are approved. Please refer to the specific adhesive data sheet for application guidelines. For mechanically attached systems, please consult your SOPREMA representative for specific fastening patterns. All laps must be heat-welded to ensure a water tight seal. Any field cut seams require using SENTINEL Cut Edge Sealant.

APPLICATION



MECHANICALLY FASTENED



FULLY ADHERED

PRODUCT	SOLAR REFLECTANCE (INITIAL)	THERMAL EMITTANCE (INITIAL)	SRI (INITIAL)
SENTINEL CopperArt P150 HFB	0.86	0.81	45

QUICK FACTS

ROLL WIDTH (ft)	ROLL LENGTH (ft)	COVERAGE (ft ²)	THICKNESS (mils)	ROLL WEIGHT (lb)	ROLLS/PALLET (pallet weight)
5.5 (1.6 m)	65 (20.0 m)	344 (32.0 m ²)	60 (1.5 mm)	175 (79.3 kg)	9 (1625 lb/ 737 kg)

* Coverage rate as reported assumes installation using side and end lap recommendations.



SENTINEL[®] COPPERART P150 HFB



APPLICATIONS

ROOFING

SHEET PROPERTIES

Reinforcement	Non-woven polyester
Back surfacing	Heavy fleece backed

DIMENSIONS & MASS

PROPERTY		TEST METHOD
Thickness, mils (mm)	60 (1.5)	ASTM D4434
Net mass per unit area, lb/100ft ² (g/m ²)	51 (2,492)	ASTM D4434

PHYSICAL PROPERTIES

PROPERTY	MD	XMD	TEST METHOD
Breaking strength, lbf/in (kN/m)	100 (18)	90 (16)	ASTM D751
Elongation at break, %	260	260	ASTM D751
Seam strength (min 75% of breaking strength)	Pass	Pass	ASTM D751
Low temperature bend, @ -40°F (-40°C)	Pass	Pass	ASTM D2136
Linear dimensional change, %	<.01	<.01	ASTM D1204
Static puncture resistance, @ ≥ 33 lbf (15 kg) min	Pass	Pass	ASTM D5602
Dynamic puncture resistance, @ 20 J min	Pass	Pass	ASTM D5635
UV EXPOSURE	Cracking (7x magnification) @ 10,000 Hours	None	ASTM G154
	Discoloration (by observation) @ 10,000 Hours	Negligible	ASTM G154
	Crazing (7x magnification) @ 10,000 Hours	None	ASTM G154

* Data is represented by average values, unless noted otherwise.

