

# ALSAN® COATING

## ASPHALT BLEED BLOCKING PRIMER

Acrylic Single-component, Water-based Primer



APPLICATIONS

ROOFS

PRODUCT DATA SHEET PD 10381 - REV.220627

### QUICK FACTS:

UNIT SIZE		AMBIENT TEMPERATURE (°F)	DRY TIME* (hours)	NEXT COAT (hours)	TECHNOLOGY
5 gal. (18.9 L)	55 gal. (208 L)	50-95 (10-35°C)	4-6	>6 at 75°F(25°C) @ 50% RH	Acrylic

\*NOTE: Relative humidity and temperature will directly affect dry time.


### PRODUCT NUMBERS:

- L-ACABBPE
- L-ACABBPE-55

### DESCRIPTION & FEATURES:

ALSAN® Coating Asphalt Bleed Blocking Primer is a water-based, acrylic primer that is VOC compliant, single component and used to enhance adhesion and block bleed through discoloration from asphalt and asphalt-based substrates such as BUR, modified bitumen and asphalt cap sheets. This primer can be used with ALSAN® Coating AC 401 or ALSAN® Coating SIL 402.

### TESTING & APPROVALS:



### APPLICATION:



ALSAN® Coating Asphalt Bleed Blocking Primer can be applied using single component airless spray equipment, 3/8" or 1/2" nap roller or brush. Prior to starting application, perform an adhesion test on each surface type to ensure adequate bond can be achieved or if another primer or other specific surface preparation is required. Do not apply over wet substrates or with risk of precipitation. Protect from freezing during transit, handling, storage, and installation. Surface should be cleaned to remove any dust, dirt or debris before application.

NOTE: This product cures by water evaporation only. Low temperatures and high humidity will slow the curing process. Product should not be applied when ambient temperature is below 50°F (10°C), could fall below 32°F (0°C) within 24 hours of application, or if rain or dew is likely to occur before product dries and/or within 6 hours of application.

### STORAGE:

Always store in sealed containers in cool, ventilated and dry locations, away from direct sunlight and heat. Do not store in direct sunlight or temperatures below 50 °F (10 °C) or above 80 F (26.6 °C). ALSAN® Coating Asphalt Bleed Blocking Primer should not be stored in locations with risk of freezing.



# ALSAN<sup>®</sup> COATING

## ASPHALT BLEED BLOCKING PRIMER

Acrylic Single-component, Water-based Primer



APPLICATIONS

ROOFS

PRODUCT DATA SHEET PD 10381 - REV.220627


### TECHNICAL INFORMATION & TESTING:

APPROXIMATE COVERAGE RATES			
SUBSTRATE PROFILE	TOTAL gal/100ft <sup>2</sup> (l/m <sup>2</sup> )	MINIMUM WFT mils	MINIMUM DFT mils
SBS SHEETS, SMOOTH OR GRANULE	1.5 (0.61)	24	10.5

PHYSICAL PROPERTIES		
PROPERTY	VALUE	TEST METHOD
Solids, volume, (%)	44	ASTM D1653
Density, lbs./gal.	10.5-11.5	ASTM D1644
VOC, g/L	<50	EPA Method B
Standard Color	Light Green, Translucent	-
Shelf life, months	12	-
Clean up	Warm Soapy Water	-

### SUSTAINABILITY:



RECYCLED CONTENT PRE/POST CONSUMER +POST INDUSTRIAL = TOTAL	VOC CONTENT LOW EMITTING	WASTE RECYCLABLE/ LEVEL	COOL ROOF SRI	EPD AVAILABLE	HEALTH PRODUCT DECLARATION <sup>®</sup> FOR ALSAN <sup>®</sup> COATING ASPHALT BLEED BLOCKING PRIMER
0% TOTAL 0%	<50 g/L	NA	NA	YES Visit <a href="http://SOPREMA.US">SOPREMA.US</a> to download	 VERSION 2.2