

# ELASTOCOL<sup>®</sup> STICK

SBS Polymer Based Primer



## APPLICATIONS

ROOFING

WALLS

FOUNDATIONS

PRODUCT DATA SHEET PD10134 - REV 230331

## PRODUCT NUMBERS:

- 38745 - 5 Gal (18.9 L) Pail

## DESCRIPTION & FEATURES:

**ELASTOCOL STICK** is an SBS polymer based primer approved for use in roofing, walls and waterproofing assemblies. **ELASTOCOL STICK** is comprised of a proprietary blend of SBS polymers, solvents and additives engineered to increase adhesion of self-adhered SBS membranes on approved substrates.

- Enhances the adhesion of self-adhesive membranes
- Resistant to water, alcohol and most saline, alkaline and diluted acids solutions
- Suitable for use on a variety of substrates, including gypsum, concrete, masonry, metal, wood and mineral-surfaced membranes

## APPLICATION:



BRUSH



ROLLER



SPRAYER

Thoroughly mix **ELASTOCOL STICK** prior to application. **ELASTOCOL STICK** is applied to the approved area via brush, roller or spray equipment. **ELASTOCOL STICK** is applied at a rate of 0.7 to 1 gallon per 100 square feet over non porous substrates. Ensure primer is tacky to-the-touch, but not wet before installing overlying membrane. Primer should not transfer to the fingertips when touched.

Refer to SOPREMA's published technical literature for additional details and application requirements.

## STORAGE:

Store the container in an upright position to prevent damage. Store in a clean, dry location and cover as necessary to protect from environmental damage such as extreme cold, heat or moisture. **ELASTOCOL STICK** is a combustible material and should be kept away from open flames and other possible ignition sources during storage and use. Storage temperature range should be between 55°F (12.8°C) and 80°F (26.7°C).

## LIMITATIONS

Adequate surface preparation is the key to proper adhesion. Ensure application surface is clean, dry and free of debris prior to application.

Ambient and surface temperatures must be between 14 - 100°F (-10 - 38°C). Do not attempt application if ice, snow, moisture or dew are present.

Primer should not be left exposed for extended periods or overnight to prevent contamination. If primer becomes fully dry, dirty and tack-free, re-prime the substrate as necessary to achieve membrane adhesion.

Do not accelerate drying of **ELASTOCOL STICK** by heating it with a torch.

## TESTING & APPROVALS:



FLORIDA BUILDING CODE



NOA # 22-0706.01

## WARRANTY:

For more information refer to [www.SOPREMA.us](http://www.SOPREMA.us) or contact your SOPREMA representative.



# ELASTOCOL<sup>®</sup> STICK

SBS Polymer Based Primer



## APPLICATIONS

ROOFING

WALLS

FOUNDATIONS

PRODUCT DATA SHEET PD10134 - REV 230331

## TECHNICAL INFORMATION & TESTING:

PHYSICAL PROPERTIES		
PROPERTY	VALUE	ASTM TEST METHOD
<b>Technology</b>	Proprietary blend of synthetic polymers, solvents	-
<b>ASTM</b>	D41	
<b>Color</b>	Copper/Green	-
<b>Coverage, gal/100 ft<sup>2</sup> (L/m<sup>2</sup>)</b>	0.7-1.0 (0.3 - 0.4)	-
<b>Specific gravity at 68°F (20°C), lb/gal (kg/L)</b>	6.7 (0.79)	D2240
<b>Flash point, °F (°C)</b>	-9.4 (-23)	D92
<b>Viscosity, Brookfield @ 77°F (25°C), cP</b>	200	-
<b>Solids by weight, %</b>	24	D6511
<b>Application temperature, °F (°C)</b>	14-100 (-10 - 38)	-
<b>Storage temperature, °F (°C)</b>	55- 80 (12.8- 26.7)	-
<b>Drying time @ 72°F (50% RH), min</b>	15 - 60	-
<b>Cleanup</b>	Mineral spirits	-
<b>Shelf life, months</b>	60	-
<b>VOC content, g/L</b>	500	D2369

\* Data is represented by average values, unless noted otherwise.