


COLVENT[®] FLAM TG

Heat-welded, SBS-Modified Bitumen Vented Membrane



APPLICATIONS

ROOFING

PRODUCT DATA SHEET PDS10070 - REV 230621

PRODUCT NUMBERS:

- 00372 - 49.2 ft x 39.4 in (15.0 x 1.0 m) - Roll

DESCRIPTION & FEATURES:

COLVENT FLAM TG (torch grade) is an SBS-modified bitumen vented base ply for use in approved multi-ply membrane and flashing assemblies. **COLVENT FLAM TG** is reinforced with a tough glass fiber mat that is saturated and coated on both sides with a proprietary formulation of elastomeric styrene-butadiene-styrene (SBS) polymer modified bitumen.

- Engineered to reduce blistering associated with moisture-retentive lightweight concrete surfaces
- Underside features heat-activated ribbon strips that create venting channels between the substrate and the membrane
- Surfaced with a polyolefin burn-off film to optimize heat welding
- Meets or exceeds requirements of ASTM D6163, Type I, Grade S

USES:

COLVENT TG is used as a component in the following systems.

USE	OVERLYING MATERIAL
Field Base Ply	Heat-Welded Modified Bitumen ¹

¹ Refer to SOPREMA's SBS-Modified Bitumen Roofing Membrane Technical Manual

APPLICATION:



Prior to installation, unroll **COLVENT FLAM TG** onto the roof surface and allow to relax. Place the membrane into the desired position and back roll the product. **COLVENT FLAM TG** is then heat welded to approved substrates. Subsequent approved inter-ply or cap ply membranes are applied to **COLVENT FLAM TG** via heat welding.

Refer to the SOPREMA SBS-Modified Bitumen Membrane Roofing Technical Manual for complete application guidelines.

STORAGE:

Store rolls in an upright position to prevent damage. Store in a clean, dry location and cover as necessary to protect from environmental damage such as extreme cold, heat or moisture.

TESTING & APPROVALS:




WARRANTY:

For more information refer to www.SOPREMA.us or contact your SOPREMA representative.

COLVENT® FLAM TG

Heat-welded, SBS-Modified Bitumen Vented Membrane



APPLICATIONS

ROOFING

PRODUCT DATA SHEET PDS10070 - REV 230621

TECHNICAL INFORMATION & TESTING:

SHEET PROPERTIES

PROPERTY	VALUE
Composition	Proprietary blend of bitumen and SBS polymers
ASTM Standard	D6163, Type I, Grade S
Reinforcement	Glass fiber
Top surfacing	Polyolefin film
Back surfacing	Heat activated bitumen strips with burn-off release film

DIMENSIONS & MASS

PROPERTY	VALUE	ASTM TEST METHOD
Length , ft (m)	49.2 (15.0)	D5147
Width , in (m)	39.4 (1.0)	D5147
Coverage ,* ft ² (m ²)	147.6 (13.7)	D5147
Roll weight , lb (kg)	100 (45.5)	D5147
Rolls per pallet	20	D5147
Pallet weight , lb (kg)	2,050 (933)	D5147
Thickness (minimum) , mils (mm)	79 (2.0)	D5147
Thickness (nominal) , mils (mm)	87 (2.2)	D5147
Net mass per unit area , lb/100 ft ² (g/m ²)	64 (3,132)	D5147
Bottom coating thickness , mils (mm)	≥ 40 (1.0)	D5147

*Coverage rate as reported assumes installation using side and end lap recommendations.

PHYSICAL PROPERTIES

PROPERTY	MD	XMD	ASTM TEST METHOD
Peak load @ 0°F (-18°C) , lbf/in (kN/m)	100 (17.5)	90 (15.8)	D5147
Elongation at peak load @ 0°F (-18°C) , %	4	4	D5147
Peak load @ 73.4°F (23°C) , lbf/in (kN/m)	50 (8.8)	40 (7.0)	D5147
Elongation at peak load @ 73.4°F (23°C) , %	5	4	D5147
Ultimate elongation @ 73.4°F (23°C) , %	45	45	D5147
Tear strength @ 73.4°F (23°C) , lbf (N)	60 (267)	60 (267)	D5147
Low temperature flexibility , °F (°C)	-15 (-26)	-15 (-26)	D5147
Dimensional stability , %	< 0.1	< 0.1	D5147
Compound stability , °F (°C)	250 (121)	250 (121)	D5147

Data is represented by average values, unless noted otherwise.