


ELASTOPHENE® FLAM LS FR GR

Low-Slope, Fire Retardant, Granulated SBS-Modified Bitumen Membrane



APPLICATIONS

ROOFING

PRODUCT DATA SHEET PDS10008 - REV 230621

PRODUCT NUMBERS:

- 01264 - **32.8 ft x 39.4 in (10.0 x 1.0 m) - Roll Standard white granules (WH)**
- 05004 - **32.8 ft x 39.4 in (10.0 x 1.0 m) - Roll Highly reflective white granules (SG)**

Contact SOPREMA® Customer Service or your sales representative for other granule color options and special order requirements.

DESCRIPTION & FEATURES:

ELASTOPHENE FLAM LS FR GR (low-slope, fire retardant, granulated) is a SBS-modified bitumen membrane approved for use in roofing assemblies as a cap ply. **ELASTOPHENE FLAM LS FR GR** is reinforced with a glass fiber mat that is saturated and coated on both sides with a proprietary formulation of elastomeric styrene-butadiene-styrene (SBS) polymer modified bitumen.

- SBS rubber polymer enhances the asphalt blend adding elongation, elasticity and flexibility to the sheet
- Reinforced with a glass fiber mat that increases the membrane's strength and durability
- Granule surfacing provides added resistance to weathering and foot traffic
- Backed with a polyolefin burn-off film to optimize heat welding
- Meets or exceeds requirements of ASTM D6163, Type I, Grade G

USES:

ELASTOPHENE FLAM LS FR GR is used as a component in the following systems:

USE	OVERLYING MATERIAL
Field Cap Ply ¹	N/A

¹ Refer to SOPREMA's SBS-Modified Bitumen Roofing Membrane Technical Manual

APPLICATION:



Prior to installation, unroll **ELASTOPHENE FLAM LS FR GR** onto the roof surface and allow to relax. Position **ELASTOPHENE FLAM LS FR GR** in desired position and back roll the product. **ELASTOPHENE FLAM LS FR GR** is then heat welded to approved substrates.


Refer to the SOPREMA SBS-Modified Bitumen Membrane Roofing Technical Manual for complete application guidelines.

STORAGE:

Store rolls in an upright position to prevent damage. Store in a clean, dry location and cover as necessary to protect from environmental damage such as extreme cold, heat or moisture.

ELASTOPHENE® FLAM LS FR GR

Low-Slope, Fire Retardant, Granulated SBS-Modified Bitumen Membrane



APPLICATIONS

ROOFING

PRODUCT DATA SHEET PDS10008 - REV 230621

TECHNICAL INFORMATION & TESTING:

SHEET PROPERTIES

PROPERTY	VALUE
Elastomeric bitumen	Proprietary blend of bitumen and SBS polymers
ASTM Standard	D6163, Type I, Grade G
Reinforcement	Glass fiber
Top surfacing	Ceramic coated granules
Back surfacing	Polyolefin film
Selvage surfacing	Polyolefin film
Selvage width, in (mm)	3 (76)

DIMENSIONS & MASS

PROPERTY	VALUE	ASTM TEST METHOD
Length, ft (m)	32.8 (10.0)	D5147
Width, in (m)	39.4 (1.0)	D5147
Coverage,* ft ² (m ²)	97.9 (9.1)	D5147
Roll weight; lb (kg)	90-103 (40.7-46.8)	D5147
Rolls per pallet	25	D5147
Pallet weight; lb (kg)	2,300-2,625 (1,040-1,193)	D5147
Thickness (minimum), mils (mm)	130 (3.3)	D5147
Thickness (nominal), mils (mm)	138 (3.5)	D5147
Thickness (selvage), mils (mm)	98 (2.5)	D5147
Net mass per unit area, lb/100 ft ² (g/m ²)	98.5 (4,808)	D5147
Bottom coating thickness, mils (mm)	≥ 40 (1.0)	D5147

*Coverage rate as reported assumes installation using side and end lap recommendations.


PHYSICAL PROPERTIES

PROPERTY	MD	XMD	ASTM TEST METHOD
Peak load @ 0°F (-18°C), lbf/in (kN/m)	110 (19.3)	95 (16.6)	D5147
Elongation at peak load @ 0°F (-18°C), %	4	4	D5147
Peak load @ 73.4°F (23°C), lbf/in (kN/m)	50 (8.8)	40 (7.0)	D5147
Elongation at peak load @ 73.4°F, %	5	4	D5147
Ultimate Elongation @ 73.4°F (23°C), %	50	50	D5147
Tear strength @ 73.4°F (23°C), lbf (N)	60 (267)	60 (267)	D5147
Low temperature flexibility, °F (°C)	-15 (-26)	-15 (-26)	D5147
Dimensional stability, %	< 0.1	< 0.1	D5147
Compound stability, °F (°C)	250 (121)	250 (121)	D5147
Granule embedment, g	1.5 avg; 2.0 max for SG		D5147

Data is represented by average values, unless noted otherwise.

ELASTOPHENE® FLAM LS FR GR

Low-Slope, Fire Retardant, Granulated SBS-Modified Bitumen Membrane



APPLICATIONS

ROOFING

PRODUCT DATA SHEET PDS10008 - REV 230517

SUSTAINABILITY




COOL ROOF RATING

PRODUCT	SOLAR REFLECTANCE		THERMAL EMITTANCE		SRI	
ELASTOPHENE FLAM LS FR GR Standard white granules (WH)	0.26 initial	0.23 3 year	0.87 initial	0.90 3 year	25 initial	23 3 year
ELASTOPHENE FLAM LS FR GR Highly reflective white granules (SG)	0.70 initial	0.62* 3 year	0.90 initial	0.90* 3 year	86 initial	75* 3 year

CRRC published results for Solar Reflectance, Thermal Emittance and SRI results were tested and evaluated in accordance with ASTM C1549, C1371, E1980, D7897 and the CRRC-1 Product Rating Program Manual.

* CRRC Rapid Ratings. Refer to Cool Roof Ratings Council (CRRC).

TESTING & APPROVALS:



NOA # 20-0825.11



LARR # 26062

WARRANTY:

For more information refer to www.SOPREMA.us or contact your SOPREMA representative.