SENTINEL® P200 HFB

Polyester Reinforced, 80 mil, Fleece-Backed PVC Membrane

PRODUCT DATA SHEET PDS10301 - REV 230525





APPLICATIONS

ROOFING

PRODUCT NUMBERS:

- P305 10 x 65 ft (3.0 x 19.8 m) Roll (White)
- P305-T 10 x 65 ft (3.0 x 19.8 m) Roll (Tan)
- P305-G 10 x 65 ft (3.0 x 19.8 m) Roll (Gray)

DESCRIPTION & FEATURES:

SENTINEL P200 HFB is a high-performance, fleece-backed, thermoplastic polyvinyl chloride (PVC) membrane designed for both steep and low slope applications. SENTINEL P200 HFB is reinforced with a tenacious, anti-wicking, weft-inserted polyester fabric that is encapsulated on both sides with a proprietary thermoplastic PVC formulation. SENTINEL P200 HFB incorporates a heavy fleece-backed underside and is available in a variety of colors, including white, gray and tan.

- Formulated utilizing only the highest quality polymers and plasticizers to produce consistent and reliable welds in a variety of ambient temperatures
- Manufactured with a minimum 40 mil thickness above scrim for a 80 mil sheet for durability and weathering resistance
- Reinforced with a high-density, polyester scrim that provides superior breaking strength as well as excellent puncture and fatigue resistance
- Heavy fleece backing helps eliminate the telegraphing of fasteners and insulation seams
- Excellent resistance to inorganic chemicals and bacterial growth
- Meets or exceeds requirements of ASTM D4434, Type III

APPLICATION:





FULLY ADHERED



MECHANICALLY FASTENED

SENTINEL P200 HFB is applied to approved substrates via mechanically attached or fully adhered systems. For fully adhered systems, SENTINEL H₂O Bonding Adhesive or DUOTACK SPF are approved. Please refer to the specific product data sheet for application guidelines. For mechanically attached systems, please consult your SOPREMA representative for specific fastening patterns. All laps must be heat-welded to ensure a water tight seal.

Refer to the SOPREMA PVC Membrane Roofing Technical Manual for complete application guidelines.

STORAGE:

Store rolls in a clean, dry location and cover as necessary to protect from environmental damage such as extreme cold, heat or moisture.

TESTING & APPROVALS:













LARR # 26102

WARRANTY:

For more information refer to www.SOPREMA.us or contact your SOPREMA representative.



SENTINEL® P200 HFB

Polyester Reinforced, 80 mil, Fleece-Backed PVC Membrane



ROOFING

PRODUCT DATA SHEET PDS10301 - REV 230525

TECHNICAL INFORMATION & TESTING:

SHEET PROPERTIES				
PROPERTY	VALUE			
Technology	Thermoplastic polyvinyl chloride (PVC)			
ASTM standard	ASTM D4434, Type III			
Reinforcement	Polyester (18 x 9, weft inserted)			
Back surfacing	Heavy fleece-backed (5.5 oz/yd²)			

DIMENSIONS & MASS						
PROPERTY	VALUE	ASTM TEST METHOD				
Length, ft (m)	65 (19.8)	D4434				
Width, ft (m)	10 (3.0)	D4434				
Coverage,* ft ² (m ²)	650 (60.4)	D4434				
Roll weight, lb (kg)	354 (160.6)	D4434				
Rolls per pallet	10	D4434				
Pallet weight, lb (kg)	3,690 (1,674)	D4434				
Thickness, mils (mm)	80 (2.0)	D4434				
Thickness over scrim, mils (mm)	40 (1.0)	D4434				
Net mass per unit area, lb/100 ft² (g/m²)	49 (2,368)	D4434				

 $^{{\}it ^*Coverage\ rate\ as\ reported\ assumes\ installation\ using\ side\ and\ end\ lap\ recommendations.}$

PHYSICAL PROPERTIES								
PROPERTY	MD	XMD	ASTM TEST METHOD					
Peak load, lbf/in (kN/m)	500 (88)	350 (61)	D751					
Elongation at peak load, $\%$	30	30	D751					
Seam strength (min 75% of breaking strength)	Pass	Pass	D751					
Tear strength, lbf (N)	115 (512)	65 (289)	D751, Proc. B					
Trapezoidal tear, lbf (N)	185 (823)	155 (689)	D751					
Low temperature flexibility, $^{\circ}F$ ($^{\circ}C$)	Pass	Pass	D2136					
Dimensional stability, %	< 0.1	< 0.1	D1204					
Change in weight after immersion in water, $\%$	< 3	< 3	D570					
Static puncture resistance, @ ≥ 33 lbf (15 kg), minimum	Pass	Pass D5602						
Dynamic puncture resistance, @ 10 J, minimum	Pass	Pass	D5635					

Data is represented by average values, unless noted otherwise.

SUSTAINABILITY



COOL ROOF RATING									
PRODUCT	SOLAR REFLECTANCE		THERMAL EMITTANCE		SRI				
	INITIAL	3 YEAR	INITIAL	3 YEAR	INITIAL	3 YEAR			
SENTINEL P150 HFB (White)	0.85	0.73	0.89	0.88	108	90			
SENTINEL P150 HFB (Tan)	0.72	0.58	0.85	0.88	88	68			
SENTINEL P150 HFB (Gray)	0.46	0.38	0.89	0.89	53	42			

